

**(12) PATENT**  
**(19) AUSTRALIAN PATENT OFFICE**

**(11)** Application No. **AU 200125117 B2**  
**(10)** Patent No. **783552**

(54) Title  
Blend for masterbatches

(51)<sup>6</sup> International Patent Classification(s)  
C08L 053/02 C08J 009/00  
B65D 039/00

(21) Application No: 200125117 (22) Application Date: 2000 .12 .07

(87) WIPO No: W001/42354

(30) Priority Data

(31) Number (32) Date (33) Country  
99124497 1999 .12 .08 EP

(43) Publication Date : 2001 .06 .18  
(43) Publication Journal Date : 2001 .08 .30  
(44) Accepted Journal Date : 2005 .11 .10

(71) Applicant(s)  
Total Petrochemicals Research Feluy

(72) Inventor(s)  
Jean-Marie Mlinaric

(74) Agent/Attorney  
F B Rice and Co,Level 23,44 Market Street,SYDNEY NSW 2000

(56) Related Art  
US 4306034

AU 200125117

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

1990s. The 1990s were a decade of significant change for the world, with the end of the Cold War, the fall of the Berlin Wall, and the beginning of the end of apartheid in South Africa. The 1990s were also a decade of significant change for the United States, with the end of the Vietnam War, the fall of the Soviet Union, and the beginning of the end of the Cold War. The 1990s were a decade of significant change for the world, with the end of the Cold War, the fall of the Berlin Wall, and the beginning of the end of apartheid in South Africa. The 1990s were also a decade of significant change for the United States, with the end of the Vietnam War, the fall of the Soviet Union, and the beginning of the end of the Cold War.

**PCT**

(10) International Publication Number  
**WO 01/42354 A1**

(B1) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GR, GD, GE, GH, GM, HR, HU, IL, IN, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(B1) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GR, GD, GE, GH, GM, HR, HU, IL, IN, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(B1) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GR, GD, GE, GH, GM, HR, HU, IL, IN, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(B1) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GR, GD, GE, GH, GM, HR, HU, IL, IN, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(B1) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GR, GD, GE, GH, GM, HR, HU, IL, IN, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(B1) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GR, GD, GE, GH, GM, HR, HU, IL, IN, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(B1) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GR, GD, GE, GH, GM, HR, HU, IL, IN, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(B1) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GR, GD, GE, GH, GM, HR, HU, IL, IN, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(B1) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GR, GD, GE, GH, GM, HR, HU, IL, IN, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(B1) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GR, GD, GE, GH, GM, HR, HU, IL, IN, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

**Published:**

- With International search report.
- Before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments.

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



(54) Title: BLEND FOR MASTERBATCHES

(57) Abstract: Provided is a blend comprising: a) from 20 to 60 wt% of a thermoplastic elastomer; b) from 8 to 30 wt% of a vinylaromatic polymer; c) from 10 to 30 wt% of one or more processing aid; d) from 0 to 20 wt% of one or more additives.

---

**BLEND FOR MASTERBATCHES**

---

**Field of the invention :**

The invention concerns a blend of styrene butadiene elastomers,  
5 polystyrene, oil and additives and the use of said blend to produce molded  
closures for containers.

**Background of the invention :**

Several rubbery compositions and their applications have already been  
10 described in the prior art.

FR 2.114.383 relates to impact resistant styrene polymers having good flow  
properties and which can be easily moulded without forming fish eyes.

15 GB 2.147.906 discloses block copolymer composition comprising at least one  
thermoplastic elastomeric block copolymer, a polymer of a monoalkenyl  
aromatic hydrocarbon and a random copolymer. This composition is  
especialy suitable as shoe upper stiffener.

20 WO 96/16122 discloses a composition useful for preparing elastomeric  
articles such as films, fibers, woven and non-woven articles. The  
composition comprises thermoplastic elastomers blended with other  
polymers to improve their processing.

25 US Patent 4,308,034 relates to rubbery compositions and molded polymeric  
articles therefrom that stimulate the appearance of natural plantation crepe  
rubber. Those compositions comprise e.g. polarizing agents.

Abstract Derwent of JP 62 256 845 discloses a rubbery composition suitable  
30 for structural materials of noise insulating sheets and vibration insulators and  
for backing materials of carpets.

CONFIRMATION COPY

---

Abstract Derwent of JP 63 057 683 relates to heat resistant gasket for syringes comprising thermoplastic elastomer consisting of block copolymer, polyphenylene ether resin, paraffinic oil and polyolefin and/or polystyrene.

- 5 Abstract Derwent of JP 63 118 359 relates to thermoplastic elastomer composition for shoe sole prepared by adding process oil, inorganic filler and thermoplastic resin to thermoplastic elastomer.

- GB 1,196,127 discloses thermoplastic compositions comprising at least 75%  
10 by weight of a thermoplastic material. Those compositions are particularly useful for making sealing gaskets for container closures.

- The closure of containers, in particular wine bottles, is becoming an important issue because the supply of natural cork is not keeping up with  
15 the increased demand for wine bottling in various parts of the world.

- Several attempts have been made to replace natural cork with synthetic materials. These attempts are based on formulations that are, among others, adequate to be mixed with a blowing agent. The role of said blowing  
20 agent is to allow the creation of cells duplicating the cellular behaviour of natural cork. Among the disadvantages resulting from these attempts one can cite, for example, the lack of uniformity of the foamed resin leading to leakage of the containers, or the need to use additives such as sulfur dioxide as an oxygen scavenger that are detrimental to the quality of the  
25 contained liquid.

- Particular polymers have been used to bring an improvement. Thus US 5,855,287 describes a synthetic closure comprising hydrogenated styrene butadiene copolymers and at least 1wt% of a blowing agent.  
30 Although this closure achieves its objective it is still unsatisfactory as regards to the relatively high cost of the raw materials used.

- 3 -

Summary of the invention:

In a preferred embodiment of the present invention there is provided an improvement in terms of raw material savings while providing equal or superior mechanical properties.

5 According to the invention, there is provided a use of a blend comprising a) from 20 to 60 wt% of a thermoplastic elastomer resulting from the copolymerisation of a vinyl aromatic monomer and a conjugated diene containing from 20 to 80 wt% of the vinylaromatic polymer and 80 to 20 wt% of the butadiene polymer, and b) from 8 to 30  
10 wt% of a vinylaromatic polymer, and c) from 10 to 30 wt% of one or more processing aids and d) from 0 to 20 wt% of one or more additives. The blend is used to produce masterbatches that are suited, after being mixed with a blowing agent, for the production of closures for liquid containers, such as bottles.

15 According to the invention there is also provided a process for the production of a cork for liquid containers comprising providing a masterbatch which comprises:

(a) from 20 to 60 wt. % of a thermoplastic elastomer resulting from the copolymerization of a vinylaromatic monomer and a conjugated diene monomer containing from 80 to 20 wt. % of the vinylaromatic polymer and 20 to 80 wt. % of the  
20 conjugate diene polymer;

(b) from 8 to 30 wt. % of a vinylaromatic polymer, other than the thermoplastic elastomer of subparagraph (a);

(c) from 10 to 30 wt. % of at least one processing aid which decreases the viscosity of the masterbatch allowing improved processing speed;

25 (d) optionally up to 20 wt. % of one or more additives selected from the group consisting of lubricity agents, which improve the introduction of the cork in containers and fillers;

(e) a blowing agent; and  
molding said masterbatch to form a cork.

30

The blends in accordance with the invention can be adapted to a wide variety of processing aids, additives and blowing agents. They provide good mechanical properties and can be used in many applications requiring a tight closure for liquid containers, such as bottles.

- 3A -

Among the thermoplastic elastomers that can be used in accordance with the present invention, those of particular importance are produced according to a process operated in solution. Such process is known in the art, reference is made to EP-A-0084795 and EP-B-344140.

5

The vinylaromatic monomer that is particularly preferred is styrene and the preferred conjugated diene is butadiene.

These monomers are subjected to polymerisation in presence of initiators or catalysts that are generally non branched or branched alkylolithium with 3 to 8 carbon atoms. However, n- and s-butyllithium are preferably used.

10

4  
5  
6  
7  
8  
9  
10  
11  
12  
13  
14  
15  
16  
17  
18  
19  
20  
21  
22  
23  
24  
25  
26  
27  
28  
29  
30  
31  
32  
33  
34  
35  
36  
37  
38  
39  
40  
41  
42  
43  
44  
45  
46  
47  
48  
49  
50  
51  
52  
53  
54  
55  
56  
57  
58  
59  
60  
61  
62  
63  
64  
65  
66  
67  
68  
69  
70  
71  
72  
73  
74  
75  
76  
77  
78  
79  
80  
81  
82  
83  
84  
85  
86  
87  
88  
89  
90  
91  
92  
93  
94  
95  
96  
97  
98  
99  
100

A coupling agent is used to allow specific molecular configuration of the resulting polymer. The coupling agent can be selected from among polyvinyl compounds, polyepoxides, polyisocyanates, polyamines, polyaldehydes, polyhalides, polyanhydrides, polyketones, polypoxiesters and polyesters.

- 5 Among the several polyfunctional agents of coupling those of small residual toxicity are preferred. For example, EP-B-344140 discloses the use of polyfunctional coupling agent of the general formula  $\text{SiX}_n\text{R}_{4-n}$  wherein X is a halogen, preferably Cl, R is an alkyl, cycloalkyl or aryl radical, preferably methyl, ethyl and/or phenyl and n is an integer from 2 to 4. The most  
10 frequently used coupling agent is  $\text{SiCl}_4$ . It is also known to use organic coupling agents carrying epoxy groups. Polymers of epoxidized hydrocarbons are used such as epoxidized vegetable oils such as epoxidized soybean oil and epoxidized linseed oil.

- 15 The styrene butadiene elastomer can be further subjected to an hydrogenation treatment to remove the remaining double bonds giving a copolymer of polystyrene-polyethylene-butylene-polystyrene.

- The amount of styrene in the elastomer can vary between 25 and 80 wt%  
20 which in combination with the coupling agent allows to select required characteristics such as hardness, elongation and strength.

- The presence of 8 to 25wt% of a vinyl aromatic polymer, preferably polystyrene is also required. A mixture of high impact polystyrene and  
25 general purpose polystyrene is preferred to reach the required hardness.

The presence of between 15 to 27 wt% of a processing aid is required. Several oils can be used, such as a mixture of naphthenic and paraffinic oil. The role of these aids is to decrease the viscosity of the masterbatch allowing improved processing speed.

- 30 Optionally, one or more of up to 20 wt% additives can be used. Some additives also called fillers are used to decrease the production cost of the

masterbatch. Among the many fillers known to those skilled in the art a preferred material is calcium carbonate in an amount of less than 15 wt%, preferably less than 10 wt%. Some other additives also called lubricity agents are used to improve the introduction of the cork in the containers.

5 Among the lubricity agents we can cite salts of fatty acids such as calcium stearate.

Present blend is particularly suited to be mixed with blowing or foaming agents allowing the production of cells within the closure. These agents can

10 be of the chemical or physical type or a combination thereof. Among the chemical agents one can cite diazoaminobenzene, benzene sulfonic acid hydrazide, N,N'-dimethyl -N,N' -dinitroterephthalamide, azobisisobutyronitrile, tetramethylene dinitrosodimethylurethane, p,p-oxybis(N-nitroso-N-methyl)benzenesulfonamide, urea-biuret (33:67),  $\beta$ -

15 naphthalene sulfonic acid hydrazide, sodium bicarbonate-citric acid (4:3), sodium bicarbonate-melamine (95:5), benzene-1, 3-disulfonic acid dihydrazide, 1,8-di-n-decyl azobisformamide, biphenyl-4,4'-di(sulfonyl azide), benzene sulfonic acid N-phenyl hydrazide, diphenyl sulfone-3,3'-disulfonyl hydrazide, p,p'-oxybis(benzenesulfonyl hydrazide), 1,6-diphenyl

20 azobisformamide, dinitrosopentamethylene tetramine, azodicarbonamide, p,p'-oxybis(benzenesulfonyl semicarbazide), barium azodicarboxylate. Among the physical type, one can cite hydrogen, air, nitrogen, carbon dioxide, water vapor, hydrocarbons, oxygen-containing aliphatics, chlorinated hydrocarbons, chlorofluorohydrocarbons. A particularly preferred agent is a polyacrylonitrile

25 polymer bead containing isobutane.

This compound is available in the commerce under the trade name of Expancell manufactured by AKZO of the Netherlands.

Surprisingly, the inventor has observed that the present blends allow to

30 reach high mechanical properties while being able to be mixed with a variety of foaming agents. The blend is therefore an ideal candidate for



- 6 -

several applications within the field of closures for liquid containing packages.

- Throughout this specification the word "comprise", or variations such as "comprises" or "comprising", will be understood to imply the inclusion of a stated element, integer or step, or group of elements, integers or steps, but not the exclusion of any other element, integer or step, or group of elements, integers or steps.

- Any discussion of documents, acts, materials, devices, articles or the like which has been included in the present specification is solely for the purpose of providing a context for the present invention. It is not to be taken as an admission that any or all of these matters form part of the prior art base or were common general knowledge in the field relevant to the present invention as it existed before the priority date of each claim of this application.

- The following example illustrate the invention. However, this example is given merely by way of guidance and does not imply any limitations.

Example :

Several blends were prepared incorporating styrene butadiene elastomers.

- Finaprene 507 is a linear SBS containing 73% PS. Its MFI at 190°C/5kg is of 7.5g/10 min.

Finaprene 435 is a radial SBS (SiC14 coupling) containing 31% PS.

Finaprene 602F is a radial SBS (Vikoflex coupling) containing 40% PS. Its MFI at 190°C/5 kg is of 8.5 g/10 min.

25

<u>Composition</u>	<u>Wt%</u>			
Finaprene 507	25	22.5	50	23.9
Finaprene 435	-	22.5	-	23.9
Finaprene 602F	25	-	-	-
General purpose polystyrene	12.5	10	10	10.6
High impact polystyrene	10	10	10	16
Oil	20.5	23	23	24.5
CaCo <sub>3</sub>	7	7	7	-
Calcium stearate	-	-	-	1.1

- 6A -

**Mechanical properties**

Hardness (Shore H)	84	86	97	89
DIN abrasion (mm <sup>3</sup> )	200	200	280	200
MF1 5 kg/190° C (g/10 min)	116	85	100	85
Tensile strength (Mpa)	7.5	7.5	9	7.5
Elongation (%)	260	340	380	340

B  
R  
I  
C  
E

The following methods have been used for measuring the properties appearing in these examples :

1. Hardness Shore : ASTM-D 2240
- 5 2. Abrasion : DIN 53516
3. Melt Flow (MI5) : ASTM-D 1238 revised 89, at 190°C and under a load of 5 kg.
- 10 4. Tensile and Elongation : ASTM-D 412, D 638, D 882

15

20

25

30

- 8 -

## THE CLAIMS DEFINING THE INVENTION ARE AS FOLLOWS:

1. A process for the production of a cork for liquid containers comprising providing a masterbatch which comprises:
  - 5 (a) from 20 to 60 wt. % of a thermoplastic elastomer resulting from the copolymerization of a vinylaromatic monomer and a conjugated diene monomer containing from 80 to 20 wt. % of the vinylaromatic polymer and 20 to 80 wt. % of the conjugate diene polymer;
  - (b) from 8 to 30 wt. % of a vinylaromatic polymer, other than the thermoplastic
  - 10 elastomer of subparagraph (a);
  - (c) from 10 to 30 wt. % of at least one processing aid which decreases the viscosity of the masterbatch allowing improved processing speed;
  - (d) optionally up to 20 wt. % of one or more additives selected from the group consisting of lubricity agents, which improve the introduction of the cork in
  - 15 containers and fillers;
  - (e) a blowing agent; and
  - molding said masterbatch to form a cork.
2. The process according to claim 1, wherein the thermoplastic elastomer is
- 20 composed of styrenic and butadienic units.
3. The process according to either claim 1 or claim 2, wherein the amount of styrene in the elastomer is between 25 to 80 wt. % and the amount of butadiene in the elastomer is from 75 to 20 wt. %.
- 25 4. The process according to any one of claims 1 - 3, wherein the vinylaromatic polymer is polystyrene.
5. The process according to claim 4, wherein the polystyrene is a mixture of high
- 30 impact and general purpose polystyrene in an amount from 8 to 25 wt. %.
6. The process according to any one of claims 1 - 5, wherein the processing aid is a mixture of naphthenic and paraffinic oil in an amount of 15 to 27 wt. %.
- 35 7. The process according to any one of claims 1 - 6, wherein the lubricity agent is calcium stearate.

- 9 -

8. The process according to any one of claims 1 - 7, comprising a filler in an amount of less than 10%.
9. The process according to claim 8, wherein the filler is calcium carbonate.
- 5 10. The process according to any one of claims 1 - 9, wherein the blowing agent is a physical blowing agent.
- 10 11. The process according to claim 10 wherein the blowing agent is a polymer bead containing isobutane.
12. A process according to claim 1, substantially as herein described.

Dated this twenty-first day of September 2005

Total Petrochemicals Research Feluy  
Patent Attorneys for the Applicant:

F B RICE & CO

15